

Silvagrip

2310 S Dock St
 Palmetto, FL 34221

Attention: Chuck Ligon

FP2260 per ASTM D3330 Peel Adhesion of Pressure Sensitive Tape

Method: Modified to test at 150deg F and 250deg F. Compare 3M and Silvagrip

Sample Preparation: Cut 1" Wide Sample Strips, Remove backing, apply to stainless steel test panel and rolled with 20lb weight twice. Set for 72hrs.

Results: Average, High, and Low Peel in grams

Test Location: Thwing-Albert, West Berlin, NJ

Technician: Steve Calamito



**Thwing-Albert
 Instrument Company**

Peel Test at 150 & 250 Degree Farenheit				
	Silvagrip		3M	
	150F	200F	150F	200F
Average	958g	476g	542g	379g
High	1101g	878g	595g	506g
Low	857g	237g	376g	299g
Std. Dev.	57.76	202.75	134.60	47.55

